



VINC+

- Recommended for still wines with a shelf-life of up to 5 years



SENSORY PROPERTIES

Releasable TCA - TCA Taint Free ⁽¹⁾ (ISO 20752)

DIMENSIONAL PROPERTIES

Length (standard): 44 / 49 / 54 mm (+/- 0.5) | **AQL - 4.0** (ISO 9727-1; ISO 2859; ISO 16420)

Diameter (standard): 24 mm (+/- 0.3) | **AQL - 1.5** (ISO 9727-1; ISO 2859; ISO 16420)

PHYSICAL PROPERTIES

Granule size: 0.5 - 1.0 mm | **AQL - N.A.** (Internal Method)

Density: 250 - 300 kg/m³ | **AQL - 4.0** (ISO 9727-2; ISO 2859; ISO 16420)

Moisture content: < 7.0% | **AQL - 2.5** (ISO 9727-3; ISO 2859; ISO 16420)

Torsion: ≥ 22 daN.cm | **AQL - N.A.** (NP 2803-6; ISO 2859)

Extraction force ⁽²⁾: 15 - 35 daN | **AQL - N.A.** (ISO 9727-5; ISO 2859)

Oxidants: N.D. | **AQL - N.A.** (Internal Method)

OTR ⁽³⁾ - 0.0017 ml/day

AVAILABLE WASHES AND CUSTOMIZATION



Printing to simulate natural cork features is available.

L02

100% of our granules undergo the *Vapex*[®] process.

⁽¹⁾ Below 0.5 ng/L with AQL 0.65 between 0.5-1.0 ng/L | ⁽²⁾ Lots > 10,000 corks | ⁽³⁾ Oxygen transfer rate
N.D. - Not detectable | N.A. - Not applicable | AQL - Acceptable Quality Level

Edition: March 2019