



VINC CUVÉE

- Superior gas retention performance



SENSORY PROPERTIES

Releasable TCA - TCA Taint Free⁽¹⁾ (ISO 20752)

DIMENSIONAL PROPERTIES

Length (standard): 48 mm (+/- 0.5) | **AQL - 4.0** (ISO 9727-1; ISO 2859; ISO 16420)

Diameter (standard): 30.5 mm (+/- 0.3) | **AQL - 1.5** (ISO 9727-1; ISO 2859; ISO 16420)

PHYSICAL PROPERTIES

Granule size: 0.5 - 2.0 mm | **AQL - N.A.** (Internal Method)

Density: 245 - 305 kg/m³ | **AQL - 4.0** (ISO 9727-2; ISO 2859)

Moisture content: < 7.0% | **AQL - 2.5** (ISO 9727-3; ISO 2859)

Torsion: ≥ 40 daN.cm | **AQL - N.A.** (NP 2803-6; ISO 2859)

AVAILABLE WASHES



L04

100% of our granules undergo the *Vapex*[®] process.

⁽¹⁾ Below 0.5 ng/L with AQL 0.65 between 0.5-1.0 ng/L

N.A. - Not applicable | AQL - Acceptable Quality Level

Edition: March 2019